



# **Thin Brick Code Compliance**

General Shale's Old Brick Originals™ thin brick veneer systems when installed as an adhered veneer application comply with the requirements of all current model building codes.



## Comply with the following codes:

- 2018 International Building Code (IBC) (Section 1404.10)
- 2018 International Residential Code (IRC) (Section 703.12)
- 2016 Building Code Requirements for Masonry Structures, Masonry Standards Joint Committee Code, ACI-530-05/ASCE 5-05/TMS 402-05 (Sections 12.1, 12.3, and Article 3.3.C)

### Description

General Shale brick is natural material with the same range and texture as full bed brick. Thin brick has an average thickness of ½". The maximum product weight is less than 15 psf.

### **Applications**

General Shale thin brick is applicable for installations to wood stud frame, metal stud frame, exterior rated cement board, concrete masonry, and poured concrete construction. Polymer modified mortars are preferred, however, type S mortar conforming to ASTM C 270 can also be used. In hot weather, type N may also be used for better workability. Thin brick units should not be installed when ambient temperatures are below 40°F unless cold weather masonry construction requirements per ACI 530.1-16 Section 1.8C are followed.

#### **Masonry Applications**

Thin brick may be installed directly to new concrete masonry units (CMU) or concrete surfaces. No metal lath or water- resistive barrier is required with these applications. Previously exposed surfaces that have been stained, sealed, painted, or treated should be sand blasted to insure proper mortar bond. Thin brick units shall be set in a  $^{1}/_{2}$ " to  $^{3}/_{4}$ " setting bed of type S mortar. To set thin brick units, fully butter the back side and set in place. Allow the brick to set for 24 hours before grouting. Use a grout mixture that is the same mortar type and tool when thumbprint hard.

### **Wood or Metal Frame Applications**

Installation shall include a water-resistive vapor-permeable barrier with a performance at least equivalent to two (2) layers of grade D paper. Preferred application is the Laticrete MVIS system adhered to cement board using Laticrete Thin Brick Mortar and a drainage mat. For additional installation details, reference the applicable MVIS Technical Bulletin (linked at the end of this document). As an alternate, a properly installed lath and scratch method can be used. Corrosion resistant metal lath and corrosion resistant lath attachments shall be installed in accordance with ASTM C 1063 every 6" on center. Metal lath shall conform to ASTM Specification for Metal Lath C 847. Apply a  $^3/_8$ " to  $^1/_2$ " thick scratch coat to metal lath. Use a  $^1/_4$ " notched trowel and leave all notches horizontal. Allow scratch coat to cure a minimum of 24 hours. Set thin brick units in a  $^3/_8$ " to  $^3/_4$ " thick setting bed applied

Tech\_Bulletin\_Thin\_Brick\_Compliance

5.6.20 **1** | Page

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. Because of the variations in methods, conditions and equipment used in various forms of masonry installing, cleaning, and / or repairing, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. GENERAL SHALE BRICK, INC. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond GENERAL SHALE BRICK, INC. direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Please consult a building professional before installing, cleaning or repairing any masonry product.

General Shale Brick, Inc. / 3015 Bristol Highway, Johnson City, Tennessee 37602 / 800.414.4661 © 2014 General Shale Brick Inc., All rights reserved. All marks are the property of General Shale Brick, inc. • www.generalshale.com





# **Thin Brick Code Compliance**

over scratch coat. The entire back surface of the brick must be covered with mortar. Total mortar thickness behind thin brick units shall not exceed  $1^{1}/4^{1}$ . Allow the brick to set for 24 hours before grouting. Use a grout mixture that is the same mortar type and tool when thumbprint hard.

### Workmanship

It is essential that all voids are eliminated. The back of every brick must be completely embedded in mortar. Joints (3/8" recommended) must be full and well tooled. Dry stack patterns are NOT recommended.

### **Estimating**

General Shale's thin brick is packaged as flats and corners as follows:

Package Size	Flat Units	Corner Units
Вох	7 sq. ft.	5 linear ft. (approx. 3.75 sq. ft.)

Quantities based on 3/8" mortar joint. Adjust quantities for corner unit coverage as indicated above.

## Cleaning

In general, thin brick units should be kept clean as work progresses. Mortar smears should be removed by gentle dry brushing at the end of work periods. For general cleaning, bucket and brush hand cleaning methods described in BIA Technical Note #20, with non-acidic detergent cleaners is recommended. Pressure wash cleaning methods should not be used.

This product is made from natural materials. Some variation in color or texture may occur, and no warranties apply. General Shale brick and all product color names listed are trademarks of the General Shale company. Material Safety Data Sheets are available on request.

### **MVIS Technical Bulletins**

Thin Rock Installation Guide (USA Interior Residential) MVIS System

Thin Rock Interior Commercial New Construction MVIS System

Thin Veneer Installation Guide (USA Exterior Residential) MVIS System

Thin Veneer Installation Guide (USA Exterior Residential) MVIS System Without Sheathing

Thin Veneer Installation Guide (USA Interior Residential) MVIS System

Tech\_Bulletin\_Thin\_Brick\_Compliance

5.6.20 **2** | Page

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. Because of the variations in methods, conditions and equipment used in various forms of masonry installing, cleaning, and / or repairing, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. GENERAL SHALE BRICK, INC. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond GENERAL SHALE BRICK, INC. direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Please consult a building professional before installing, cleaning or repairing any masonry product.